

CODE:801 (FSC)

80g COATED PAPER/REMOVABLE ADHESIVE PLUS A-02/WHITE CCK



Application

- Minimum labeling temp: 0°C.
Service temp : -20°C~80°C. (24h after labeling)
- Suitable for bar code printing, blank die-cutting label in conventional gloss.
- Rough surface substrate is not recommended.
- Due to different substrate and applicate environment, after labeling 3 months the adhesive viscosity may increase and transform to permanent, or viscosity decline. Some substrate may have strong chemical reaction with removable adhesive, full test is recommended before use.

印刷及加工

- Suitable for conventional printing.
- Full page printing is not recommend.
- To keep the removable performance of label, applicate in over 70°C environment and tag to plexiglass(PMMA), PVC,PET and PP surface is not recommended. Due to the vary of paper substrate, pretest is recommended.

Shelf life

From date of manufacture:12 months, storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

Facestock

Coated paper , glossiness between matte & high gloss.

Indicator	Parameter	Unit	Method
Substance	80±5%	g/m ²	ISO536
Caliper	70±5%	μm	ISO534

Adhesive

Removable acrylic adhesive

Liner

White CCK

Indicator	Parameter	Unit	Method
Substance	80±10%	g/m ²	ISO536
Caliper	80±10%	μm	ISO534
Tensile strength MD	≥5.4	kN/m	ISO 1924-2

Performance

Indicator	Parameter	Unit	Method
Initial Tack	6-12	N/25mm	FTM9, ss
90° Peel Adhesion (20min)	4-10	N/25mm	FTM2, ss
Shear Min.	≥3	hour	FTM8, ss
Release force	10-40	G/25mm	FTM4, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of finally explanation.