



# **CODE: S09**

## $50\,\mu\,\text{m}$ MATT WHITE PET/MEMBRANE GLUE C-01/80g WHITE GLASSINE





## Application

- Minimum labeling temp: -5°C. Service temp: -20°C~100°C. (24h after labeling)
- Suitable for all kinds of permanent label and special purpose daily chemical products label.

## Print & Process

Suitable for most of printing methods and thermal transfer printing, and use UV ink, water-based ink, special purpose solvent ink for PET. Ink test before printing is recommended. To avoid the adhesive overflow, sharp film specialty die-cutting knife is recommended.

#### Shelf life

From date of manufacture:12 months, storage conditions:  $23\pm2^{\circ}$ C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

#### **Facestock**

The facestock have special printability coated, have a certain resistance to routine chemical, high-temperature, scratch, moisture and fouling. Suitable for all kinds of permanent label.

Indicator	Parameter	Unit	Method
Caliper	$50\pm5\%$	μm	I \$0536
Substance	$70 \pm 5\%$	g/m²	I \$0534

## Adhes i ve

General purpose membrane emulsion acrylic adhesive

#### Liner

Super calendered thick white glassine

Indicator	Parameter	Unit	Method
Substance	80±5%	g/m²	IS0536
Caliper	$70 \pm 5\%$	μш	IS0534
Tensile Strength MD	≥6	kN/m	ISO 1924-2

## Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥8	N/25mm	FTM9, ss
90° Peel Adhesive (20min)	≥5	N/25mm	FTM2, ss
Shear Min.	≥15	hours	FTM8, ss
Release force	10~40	G/25mm	FTM4,ss

## Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of final explanation.