

# we will provide you with faster and more professional value-added services

# CODE: S572

50um METALIZE Bopp (INNER COATING) FILM/MEMBRANE GLUE C-01/80g WHITE GLASSINE



# **Application**

- Minimum labeling temp: -5℃.
  Service temp: -20℃~100℃. (24h after labeling)
- Suitable for daily chemical products label, personal hygiene products label and promotional label.
- Not recommended to be used in irregular curved surface and extra soft bottle because the facestock is stiffer.
- Not recommended for occasions with duplicate paste requirement.

# Print & Process

- With special treatment coating, can be used in relief printing, flexography printing, gravure printing, screen printing and varieties of printing methods. Suitable for UV ink and water-based ink.
- Control the viscosity of print ink, high contractility bring label crimp, cause the label detach from release paper or warp from label object.
- Excellent performance at bronzing.
- Sharp special die-cut knife for film is recommended especially platen die cut.

# Shelf life

From date of manufacture:12 months, storage conditions:  $23\pm2^{\circ}$ C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

#### **Facestock**

A kind of high metal gloss BOPP film with special printability coating.

Indicator	Parameter	Unit	Method
Substance	$45\pm5\%$	$g/m^2$	ISO 53 <b>6</b>
Caliper	$50 \pm 5\%$	μm	ISO 534

# Adhesive

General purpose membrane emulsion acrylic adhesive

# Liner

Super calendered thick white glassine

Indicator	Parameter	Unit	Method
Substance	80±5%	g/m²	ISO 53 <b>6</b>
Caliper	$70 \pm 5\%$	μш	ISO 534
Tensile strength MD	≥6	kN/m	ISO 1924-2

#### Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥8	N/25mm	FTM9, ss
90° Peel Adhesion (20min)	≥5	N/25mm	FTM2, ss
Shear Min.	≥15	hours	FTM8, ss
Release forc	e 10~40	G/25mm	FTM4,ss

### Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of final explanation.