

CODE: HPW561J (original code 561J)
60μm White Bopp Film/Acrylic Plus/White Glassine

Application

Fulfill the requirement of ROHS, REACH, VOC

- Minimum labeling temp: -5°C
Service temp: -20°C~80°C (24h after labeling)
- Suitable for application of daily chemical label & food label.
- Facestock has special soft pearly gloss, and excellent process performance.
- Must test to confirm if used in small bottle label (diameter smaller than 30mm).

Print & Process

- Suitable for conventional printing.
- Control the viscosity of print ink. High contractility will cause the label to curl, resulting in detachment from the liner or warping on the affixed object.
- Lest the pattern fades, printed label without film should try to avoid contact with solvents such as alcohol, isopropanol, gasoline, toluene, etc.
- Sharp special die-cut knife for film is recommended.

Shelf life

From date of manufacture: 12 months
 Storage conditions: 23±2°C & relative humidity 50±5%.
 Prolonged storage outside these conditions might reduce the shelf life.

Facestock

A fine pearled BOPP film with special printability coated.

Indicator	Parameter	Unit	Method
Substance	45±5%	g/m ²	ISO 536
Caliper	60±5%	μm	ISO 534
Glossiness	≥85	%	ASTM D2457(60°)

Adhesive

General purpose acrylic adhesive of film

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m ²	ISO 536
Caliper	51±5%	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥9	N	FTM9, ss
90°Peel Adhesion (20min)	≥5.5	N/25mm	FTM2, ss
Shear Strength	≥15	hours	FTM8, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.