

心更快更专业的增值服务于你

CODE: HS501 (original code 501)

54µm Synthetic Paper/Acrylic adhesive/White Glassine





Application

Fulfill the requirement of ROHS, REACH, VOC

- Minimum labeling temp: -5°C
 Service temp: -20°C~80°C (24h after labeling)
- Suitable for aviation or railway baggage tag, high quality logistics tag etc.
- Not recommended for bottles with irregular surfaces or with extrusion resistance requirements.

Print & Process

- With special treatment coated, have an excellent performance in printing and bar code printing, good stiffness, easy to peel off. Can be used in carbon ribbon printing, screen printing, rotary letterpress, offset lithography, etc. Suitable for UV ink, oil-based ink and water-based ink.
- Not suitable for inks containing alcohol or volatile organic solvents.
- Avoid to print to the edge of label, especially when using screen UV ink and UV finish, the high-contractility bring label crimp, causing the label detach from release paper or warp from label object. Ink testing before printing is recommended.

Shelf life

Tel.: +86-021-69788081

From date of manufacture: 12 months Storage conditions: $23\pm2^{\circ}$ C & relative humidity $50\pm5\%$. Prolonged storage outside these conditions might reduce the shelf life.

Guangdong Youhua New Material Technology Co., Ltd.

Facestock

The facestock have special printability coated, both like paper printability and BOPP film physical characteristics, suitable for common color printing and ribbon printing.

Indicator	Parameter	Unit	Method
Substance	$54 \pm 5\%$	μm	ISO 534
Whiteness	≥92	%	TAPPI T-525
Opacity	≥80	%	TAPPI T-525

Adhesive

General-purpose film acrylic adhesives This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	$58\pm5\%$	g/m^2	ISO 536
Caliper	$51\pm5\%$	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥ 8	Ν	FTM9, ss
90°Peel Adhesion (20min)	' ≥5	N/25mm	FTM2, ss
Shear Strength	≥15	Н	FTM8, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China Tel.: +86-769-88882212 Shanghai Xinyouhua New Material Technology Co., Ltd. Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China