

以更快更专业的增值服务于你

CODE: YA027 (original code 027)

70g Matt Art paper/Acrylic adhesive/White Glassine



Application

Fulfill the requirement of ROHS, REACH, VOC

- Minimum labeling temp: +5°C
 Service temp: -20°C~80°C (24h after labeling)
- Suitable for conventional glossy food information labels, blank ribbon printing labels, etc.
- Must test to confirm if used in small bottle label (diameter smaller than 30mm).
- Rough surface substrate is not recommended.

Print & Process

- Suitable for conventional printing.
- Full page printing is not recommended.
- Ribbon printing. There are various types of printers and carbon ribbons, must be tested first.

Shelf life

From date of manufacture: 12 months

Storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

Facestock

A kind of super calendered art paper with smooth surface.

Indicator	Parameter	Unit	Method
Substance	$70\pm5\%$	g/m^2	ISO 536
Caliper	$61\pm5\%$	μm	ISO 534
Whiteness	≥85	%	ISO 2470

Adhesive

High-viscosity permanent acrylic emulsion adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	$58\pm5\%$	g/m²	ISO 536
Caliper	$51 \pm 5\%$	μт	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥14 or PT	N	FTM9, ss
90°Peel Adhesion (20min)	≥7 or PT	N/25mm	FTM2, ss
Shear Strength	≥3	Н	FTM8, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China

Tel.: +86-769-88882212

Shanghai Xinyouhua New Material Technology Co., Ltd.

Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China Tel.: +86-021-69788081

VER 3.0

Release: Dec., 2024