

心更快更专业的增值服务于你

CODE: YA208 (original code 208)

80g Art Paper/Hot melt adhesive/White Glassine



Application

Fulfill the requirement of ROHS, REACH

- Minimum labeling temp: -5°C
 Service temp: -20°C~70°C (24h after labeling)
- Suitable for Food or Medicine labels in conventional gloss.
- Can be applied to the flat and curved surfaces of most substrates. Sample testing is recommended first.

Print & Process

- Suitable for conventional printing.
- Control the viscosity of print ink, to avoid heavy viscosity cause coating exfoliation.
- For fine barcode printing, comprehensive print test is required.

Shelf life

From date of manufacture: 12 months Storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

Facestock

Art paper, glossiness between matte & high gloss.

Indicator	Parameter	Unit	Method
Substance	80±5%	g/m²	ISO 536
Caliper	70±5%	μm	ISO 534

Adhesive

General purpose permanent hot melt adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m	ISO 536
Caliper	51±5%	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥19 or PT	Ν	FTM9, ss
90° Peel Adhesion (20min)	≥ 9.5 or PT	N/25mm	FTM2, ss
Shear Min	≥10	Н	FTM8, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd. Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China Tel.: +86-769-88882212

Shanghai Xinyouhua New Material Technology Co., Ltd. Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China Tel.: +86-021-69788081 **VER3.0**