


以更快更专业的增值服务于你

CODE: YA853 (original code S853)

80g Art Paper/Freezing hotmelt/Yellow Glassine





Application

Fulfill the requirement of ROHS, REACH

- Minimum labeling temp: -25°C Service temp: -50°C~50°C (24h after labeling)
- Suitable for Food, Medicine or Refrigerated Product label in conventional gloss, etc.
- Must test to confirm if used in small bottle label (diameter smaller than 30mm).
- Good initial and final adhesion at low temperatures, with excellent performance on many packaging materials. Recommended for use at low temperatures.
- Not suitable for application on PVC surfaces.

Print & Process

- Suitable for various printing methods such as offset, gravure, and flexographic printing.
- Control the viscosity of the ink to avoid coating detachment caused by excessively sticky ink.
- Not recommended to process die cutting in environment above 20 °C to avoid adhesive overflow.

Shelf life

From date of manufacture: 12 months

Storage conditions: 20±2°C & relative humidity 50±5%. Prolonge storage outside these condition might reduce the shelf life.

Facestock

Art paper, glossiness between matte & high gloss.

Indicator	Parameter	Unit	Method
Substance	80±5%	g/m^2	ISO 536
Caliper	$70 \pm 5\%$	μш	ISO 534

Adhesive

Freezing hot melt adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered yellow glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m^2	ISO 536
Caliper	51±5%	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

	Indicator	Parameter	Unit	Method
	Initial Tack	≥11 or PT	N	FTM9, ss
9	0° Peel Adhesion (20min)	≥6 or PT	N/25mm	FTM2, ss
	Shear Strength	≥8	hours	FTM8, ss
L	ow-temperature Loop Tack	≥17 or PT	N	±5℃, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China

Tel.: +86-769-88882212

Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China Tel.: +86-021-69788081

Release: Dec., 2024

VER 3.0

Shanghai Xinyouhua New Material Technology Co., Ltd.