

CODE: YT402 (original code 402)

70g Top Coated Thermal Paper/Hot melt adhesive/ White Glassine





Application

Fulfill the requirement of ROHS, REACH

- Minimum labeling temp:-5℃
- Service temp: -20°C ~70°C (24h after labeling)
- Suitable for logistics tag.
- Suitable for fine bar code printing.
- Application environment above 50°C or direct sunlight are not applicable.

Print & Process

- Suitable for conventional printing.
- Alcohol or volatile organic solvent inks are not applicable.

Shelf life

From date of manufacture: 9 months Storage conditions: 23±2°C & relative humidity 50±5%. According to the thermal paper properties, please try to avoid keeping the product in high temperature, high humidity, alcohol, oil, plasticizer.

Facestock

Top coated thermal paper, with good performance at resistance of water, oil, plasticizer and scratch.

| Indicator | Parameter | Unit | Method |
|-----------|------------|---------|------------|
| Substance | $70\pm5\%$ | g/m^2 | ISO 536 |
| Caliper | $72\pm5\%$ | μm | ISO 534 |
| Optical | ≥1.10 | | GB/T 28210 |

Adhesive

General purpose permanent hot melt adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

| Indicator | Parameter | Unit | Method |
|-----------------|------------|---------|----------|
| Substance | $58\pm5\%$ | g/m^2 | ISO 536 |
| Caliper | $51\pm5\%$ | μm | ISO 534 |
| Tear Resistance | ≥300 | mN | GB/T 455 |

Performance data

| Indicator | Parameter | Unit | Method | | |
|------------------------------|-----------------|--------|----------|--|--|
| Initial Tack | ≥ 14 or PT | Ν | FTM9, ss | | |
| 90 ° Peel Adhesion(20min) | ≥7 or PT | N/25mm | FTM2, ss | | |
| Shear | ≥10 | Н | FTM8, ss | | |

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.
- We reserve the rights of finally explanation.