

CODE: YTT966 (original code 966)
70g Thermal Transfer Paper/Acrylic/White Glassine


Application

Fulfill the requirement of ROHS, REACH, VOC

- Minimum labeling temp: +5°C
Service temp: -20°C~80°C (24h after labeling)
- Suitable for food label, blank carbon belt label in conventional glossy.
- Can be used in small bottles with diameter less than 30mm. Sample testing before mass print is recommended.

Print & Process

- Suitable for conventional printing.
- Full page printing is not recommended.
- Conventional ribbon printing has excellent performance.

Shelf life

From date of manufacture: 12 months

Storage conditions: 23±2°C & relative humidity 50±5%.

Prolonged storage outside these conditions might reduce the shelf life.

Facestock

The Facestock has been super calendered, with smoothly surface.

Indicator	Parameter	Unit	Method
Substance	70±5%	g/m ²	ISO 536
Caliper	70±3	μm	ISO 534
Whiteness	≥80	%	ISO 2470

Adhesive

High viscosity permanent acrylic emulsion adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m ²	ISO 536
Caliper	51±5%	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥14 or PT	N	FTM9, ss
90°Peel Adhesion (20min)	≥7 or PT	N/25mm	FTM2, ss
Shear Strength	≥3	hours	FTM8, ss

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.