

# 以更快更专业的增值服务于你

## CODE: YW905 (original code 905)

## 70g Woodfree Paper/Acrylic/Yellow Glassine



### **Application**

Fulfill the requirement of ROHS, REACH, VOC

- Minimum labeling temp: +5°C Service temp: -20°C~80°C (24h after labeling)
- Suitable for a variety of low-gloss labels, price tags, etc.
- Rough surface substrate is not recommended.

#### **Print & Process**

- Suitable for normal color printing and inkjet printing. Due to differences in ink concentration, please do sample printing tests to confirm the printing performance first.
- Control the viscosity of ink to avoid coating detachment caused by heavy-viscosity ink.

### Shelf life

From date of manufacture: 12 months

Storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

#### **Facestock**

Woodfree paper with fine ink-absorbency.

Indicator	Parameter	Unit	Method	
Substance	$70\pm5\%$	$g/m^2$	ISO 536	
Caliper	$85\pm5\%$	μm	ISO 534	

#### Adhesive

High viscosity permanent acrylic emulsion adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

## Liner

Super calendered yellow glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m²	ISO 536
Caliper	$51 \pm 5\%$	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

#### Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥14 or PT	N	FTM9, ss
90°Peel Adhesion (20min)	≥7 or PT	N/25mm	FTM2, ss
Shear Strength	≥3	hours	FTM8, ss

#### **Statement:**

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China

Tel.: +86-769-88882212

Tel.: +86-021-69788081

Shanghai Xinyouhua New Material Technology Co., Ltd.

Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China

VER 3.0

Release: Dec., 2024