

以更快更专业的增值服务于你

CODE: YW920 (original code S920)

70g Woodfree Paper/Hot melt adhesive/ White Glassine



Application

Fulfill the requirement of ROHS, REACH

- Minimum labeling temp: -5°C Service temp: -20°C~70°C (24h after labeling)
- Suitable for a variety of low-gloss labels, price tags, etc.
- Rough surface substrate is not recommended.

Print & Process

- Suitable for conventional printing and inkjet printing.
- Control the viscosity of ink to avoid coating detachment caused by heavy-viscosity ink.

Shelf life

From date of manufacture: 12 months

Storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

Facestock

Woodfree paper with fine ink-absorbency.

Indicator	Parameter	Unit	Method
Substance	$70\pm5\%$	g/m^2	ISO 536
Caliper	$85 \pm 5\%$	μm	ISO 534

Adhesive

General purpose permanent hot melt adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

Liner

Super calendered white glassine

Indicator	Parameter	Unit	Method
Substance	$58\pm5\%$	g/m²	ISO 536
Caliper	51±5%	μт	ISO 534
Tear Resistance	≥300	mN	GB/T 455

Performance data

Indicator	Parameter	Unit	Method	
Initial Tack	≥14 or PT	N	FTM9, ss	
90°Peel Adhesion (20min)	≥7 or PT	N/25mm	FTM2, ss	
Shear Strength	≥10	hours	FTM8, ss	

Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China

Tel.: +86-769-88882212

Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China Tel.: +86-021-69788081

Release: Dec., 2024

VER 3.0

Shanghai Xinyouhua New Material Technology Co., Ltd.