

## 以更快更专业的增值服务于你

# CODE: YW925 (original code 925)

### 70g Woodfree Paper/Hot melt adhesive/ Yellow glassine



#### **Application**

Fulfill the requirement of ROHS, REACH

- Minimum labeling temp: -5°C Service temp: -20°C~70°C (24h after labeling)
- Suitable for a variety of low-gloss labels, price tags, etc.
- Rough surface substrate is not recommended.

#### **Print & Process**

- Suitable for general color printing and inkjet printing. Due to differences in ink concentration, please make samples to check and confirm printing effect first.
- Control the viscosity of ink to avoid coating detachment caused by heavy-viscosity ink.

#### Shelf life

From date of manufacture: 12 months Storage conditions: 23±2°C & relative humidity 50±5%. Prolonged storage outside these conditions might reduce the shelf life.

#### Facestock

Woodfree paper with fine ink-absorbency.

Indicator	Parameter	Unit	Method
Substance	$70\pm5\%$	$g/m^2$	ISO 536
Caliper	$85 \pm 5\%$	μm	ISO 534

#### Adhesive

General purpose permanent hot melt adhesive

This adhesive complies with FDA section 21 (175.105) and can be used for not-contact labeling of food, pharmaceutical and cosmetic products.

#### Liner

Super calendered yellow glassine

Indicator	Parameter	Unit	Method
Substance	58±5%	g/m²	ISO 536
Caliper	$51 \pm 5\%$	μm	ISO 534
Tear Resistance	≥300	mN	GB/T 455

#### Performance data

Indicator	Parameter	Unit	Method
Initial Tack	≥14 or PT	N	FTM9, ss
90°Peel Adhesion (20min)	≥7 or PT	N/25mm	FTM2, ss
Shear Strength	≥10	hours	FTM8, ss

#### Statement:

- All the statements, tech information & recommendations are based on the tests believed to be reliable but do not constitute a guarantee or warranty. All products sold should be tested by the customer in the end-use environment to confirm compliance with the requirements of that environment and to determine which materials to purchase.
- We reserve the rights of final explanation.

Guangdong Youhua New Material Technology Co., Ltd.

Add.: No.5, Eighth Road, Jiaoli East District, Zhongtang Town, Dongguan City, Guangdong Province, China

Tel.: +86-769-88882212

Shanghai Xinyouhua New Material Technology Co., Ltd.

Add.: No. 656, Huacai Road, Huaxin Town, Qingpu District, Shanghai, China

Tel.: +86-021-69788081

VER 3.0

Release: Dec., 2024